

C07 : CHEMO-FIX PLUS

Type 4TS1/ C2TES1



- For Exterior Use
- Tile On Tile
- For Large Format Tile
- Natural Stone

12/25

CHEMO - Q

PRODUCT DESCRIPTION

Chemo-fix Plus is highly polymer modified with high flexibility premium thin-set Adhesive for Installation of large format tiles, stone and glass mosaics for interior and exteriors.

PRODUCT PACKAGE & COLOR

- 20 KG Bag BOPP Double Laminated bags for maximum moisture protection
- Color : White & Grey

APPLICATION AREA

- For Interior and Exterior Both
- Floor and Wall (Tile on Tile)
- Swimming Pool, Fountains, Facades, Bathroom
- Heavy Duty Industrial & Commercial

COMPLIES/STANDARDS

As per the requirements
EN12004 & ISO 13007 - C2TES1
IS 15477 : 2019 Type 4TS1

APPLICATION SURFACE

- Cement Base Mortar Floor
- Cement Board (Dry Partition)**
- Underfloor Heating Installation
- Tile on Tile (Existing tiles/Stones)*

*Surface to be cleaned and made rough before Installation of tiles

**Consult the Dry Wall Board manufacture's Data sheet for the specific recommendations and lead Bearing capacity of specific Board intended for use.

INSTRUCTIONS FOR USE

- 1 Add water and mix mechanically until you obtain a smooth paste of workable consistency.
- 2 Leave the paste to stand for 5 minutes and mix again before applying.
- 3 Spread the paste on the surface in sections of a surface area no larger than 2 m², combing with a suitable trowel.
- 4 If double gluing is required, spread the mixture over the back of the tile as well.
- 5 Put the tiles on top of the freshly-laid adhesive, pressing lightly to ensure that the whole tile surface comes into contact with the adhesive, filling any grooves.
- 6 Leave a joint of a width of at least 2 mm between indoor tiles and at least 5 mm between outdoor tiles
- 7 Wait 24 hours before grouting wall tiles and 48 hours before grouting floor tiles.
- 8 Respect all perimeter and structural joints. Place one partition joint every 50 m² for indoor floor tiling, and one every 30 m² for outdoor floor tiling.

C07 : CHEMO-FIX PLUS

Type 4TS1/ C2TEST1

TECHNICAL FEATURES

12/25

CHEMO - Q

Appearance	Granular Powder	Tensile Adhesion Strength Dry Condition After 28 days	$\geq 1.75-2.25 \text{ N/mm}^2$
Color	White & Grey	Tensile Adhesion Strength Wet Condition @28 days	$\geq 1.50-1.85 \text{ N/mm}^2$
Powder Density	1.45-1.55 gm/cc	Ready for light traffic	24 Hours
Paste Density	1.80-2.85 gm/cc	Ready for grouting	24 Hours
Water Demand	25%-30%	Bed Thickness	3-12 mm
Pot Life	4 Hours	S-1 Deformality	$\geq 3.75 \text{ mm}$
Open Time	$\geq 35 \text{ minutes}$	Shear Adhesion Strength Dry Condition After 28 days	$1.35-1.50 \text{ N/mm}^2$
Adjustment Time	$\geq 30 \text{ minutes}$	Shear Adhesion Strength Wet Condition After 28 days	$1.25-1.35 \text{ N/mm}^2$
T-Slip Resistance	No Slip		
Mixing Time	5 - 10 Minutes		
Coverage	45-50 Sq. Ft (3 mm Bed) 25-30 Sq. Ft (5 mm Bed)		

NOTE

This test values were obtained during our laboratory tests. Site mixes may show slight difference in performance due to methods of applications and varying site conditions.

STRONG ADHESIVE FOR STRONG FOUNDATION

WARNINGS AND RECOMMENDATION

- Avoid applying on dead plaster or weak renderings.
- Do not apply this product when frost or rain are forecasted.
- Do not apply in areas where there is a risk of standing water.
- In extreme weather conditions (wind or high temperatures), the product will dry more quickly than usual. This will result in shorter open time.
- In high temperatures, windy conditions or if the application surface is very absorbent, it is advisable to moisten the surface and wait for the film of water to disappear before applying the product.
- Check, periodically, that a surface film has not formed on the adhesive paste once it has been spread onto the surface. If film has formed, remove the product and apply a fresh coat.
- Check that the paste is sticky enough by periodically lifting one of the tiles already in place to ensure that it is well suck down.
- Use within 1 year of date of packaging. Store the product in its original packaging in a dry, covered place protected from humidity.

C07 : CHEMO-FIX PLUS

Type 4TS1/ C2TES1

HEALTH AND SAFETY

Chemo Q tile adhesive is cement-based construction material. Use of gloves and goggles is recommended. Avoid eye contact and prolonged skin contact. Any splashes to the skin or eyes should be washed off with clean water. In the event of prolonged irritation, medical advice should be sought.

12/25

CHEMO - Q

DISCLAIMER-

Information on this datasheet is to be treated as guideline for usage. Users are advised to undertake a trial for product suitability prior to full-scale usage. There is no express or implied warranty/guarantee for results. The company is not liable for any consequential damages.

FOR MORE INFORMATION CONTACT

Reg. Address- Chemo-Q Industry, Khasra No.97/25, 2nd Mile Stone Ratia Road, Bhuna (125111), Dist. Fatehabad, Haryana

Contact Number- +91 9671673456

Email- info@chemoqindustry.in

Website- www.chemoqindustry.in