



Joint venture between SGS and IMME Mongolia

SGS-IMME Mongolia LLC.  
Уйлдхерлин тойруу, 101 тоот,  
Bayanqol District 29<sup>th</sup> khoroо,  
Ulaanbaatar Mongolia



SGS Report No.: INSOR26103



Detailed weighing list as below:


INSOR26103 [REDACTED] - 2026-06.15		
	Bag Weight (Kg)	SGS Seal No.
1	993.50	M6695173
2	997.50	M6695171
3	997.50	M6695172
4	991.50	M6695174
5	1,030.00	M6695175
total:	5,010.00	
Bag weight:	10.00	
net Weight:	5,000.00	

### MOISTURE DETERMINATION:

Moisture determination was conducted at the SGS Mongolia laboratory.

Before operation, all the facilities used for splitting gross samples and moisture determination was cleaned up with same material taken from site to avoid any pollution. After the gross sample per lot was well mixed, 2 sets x approximately 2.0kg samples for moisture tests were taken by 20 increments division method.

Duplicate moisture samples were weighed, dried in the thermostatic oven at temperature of 105°C+/-5°C for 12 hours. The samples were placed back into the oven for another hour to get a constant weight. The calculated average mass loss for the duplicate samples is reported.



This document is issued by the Company under its General Conditions of Service accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Joint venture between SGS and IMME Mongolia

**SGS-IMME Mongolia LLC.**

Улс төрийн тойргуу, 101 тоот,  
Баянгол Дистрикт 29<sup>м</sup> хороо,  
Улаанбаатар Монголиа



**SGS Report No.: INSOR26103**

**SAMPLE PREPARATION:**

After moisture determination, the moisture sample was used as the quality sample preparation.

The dried quality sample was crushed to 1 mm and well mixed and divided to get approximately 500g sample, then the 500 grams sample was pulverized by steel roly until the >95% sample pass the 200 mesh, Then the samples were sent to the SGS UB Laboratory for testing.

**ANALYSIS:**

In accordance with instructions received from applicants, we prepared and carried out required test on the sample.

Analysis results refer to the following.


Elements	H2O	S	P	WO3	Pb	Bi	Cu
standard	CS11-02 15:2013	CS11-01 96:2013	CS11-02 14:2013	CS11-02 14:2013	CS1-02 06:2013	CS1-02 06:2013	CS1-02 06:2013
METHOD	PHY08D	CSA06V	IC40A	XRF76V	ICM40B	ICM40B	ICM40B
UNITS	%	%	%	%	PPM	PPM	PPM
MD-1	0.28	1.76	0.01	69.21	370	2110	1380

As	Mo	Sn	Sb	U	Th	Fe	Cr
CS11-0206:2013	CS11-0 206:2013	CS11-02 14:2013	CS11- 0206:2013	CS11-2 06:2013	CS11-2 06:2013	CS1-02 06:2013	CS1-02 06:2013
ICM40B	ICM40B	IC40A	ICM40B	ICM40B	ICM40B	IC40A	ICM40B
PPM	PPM	%	PPM	PPM	PPM	%	PPM
6	20.5	0.01	0.89	4.69	0.6	3.29	24

**WEATHER CONDITION:**

June 15, 2026, Sunny

The manual sampling method was agreed with the SGS Principal, as sampling by more reliable methods was not possible. The suitability of this sampling method is defined by the standard.



This document is issued by the Company under its General Conditions of Service accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.