

# SABIC® HDPE B1054M

## PROVISIONAL TECHNICAL DATA SHEET HIGH DENSITY POLYETHYLENE

### DESCRIPTION

B1054M is a High Density Polyethylene specially developed for blow molding and jerry cans. The material offers high stiffness, good processability and excellent combination of stiffness and ESCR with good impact resistance.

### TYPICAL APPLICATIONS

B1054M is specially designed for standard jerry cans for the packaging of dangerous goods, Light weight jerry cans and UN approved jerry cans.

### TYPICAL PROPERTY VALUES

Revision 20230320

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES <sup>(1)</sup></b>			
<b>Melt Flow Rate (MFR)</b>			
at 190°C and 5 kg load	0.43	g/10 min	ISO 1133
at 190°C and 21.6 kg load	9.5	g/10 min	ISO 1133
FRR (MFR 21.6kg/MFR 5kg)	22	-	ISO 1133
<b>Density</b>			
@23°C	954	kg/m <sup>3</sup>	ISO 1183
<b>MECHANICAL PROPERTIES <sup>(2)</sup></b>			
<b>Tensile modulus</b>	1200	MPa	ISO 527
<b>Tensile impact test</b>			
Tensile Impact Strength (23°C, Notched)	145	kJ/m <sup>2</sup>	ISO 8256
Tensile Impact Strength at -30°C (Notched)	≥60	kJ/m <sup>2</sup>	ISO 8256
<b>Charpy impact strength @ -30°C</b>	7	kJ/m <sup>2</sup>	ISO 179/1eU
<b>FNCT (3.5 MPa, 2 % Igepal BC/9, 80°C)</b>	>18	Hrs	ISO 16770

(1) Typical values: not to be construed as specification limits.

(2) Based on compression molded sheet. Compression moulding of test specimen according to ISO 1872-2 Conditioning of test specimen: temp. 23 °C, relative humidity 50 %, 24 hours

### PROCESSING CONDITIONS

Recommended processing temperature: 180 - 220 °C

### STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.