

# SABIC® HDPE B5403M

## PROVISIONAL TECHNICAL DATA SHEET HIGH DENSITY POLYETHYLENE

### DESCRIPTION

HDPE B5403M is a High Density Polyethylene specially developed for blow molding / Jerry cans and drums. The material offers an excellent combination of stiffness and ESCR and a high Impact resistance.

### TYPICAL APPLICATIONS

B5403M is specially designed for standard jerry cans, UN approved jerry cans, standard drums, L-ring drums for packaging of dangerous goods and UN approved open top drums.

### TYPICAL PROPERTY VALUES

Revision 20211203

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES <sup>(1)</sup></b>			
<b>Melt Flow Rate (MFR)</b>			
at 190°C and 10kg	0.5	g/10 min	ISO 1133
at 190°C and 21.6 kg	2.7	g/10 min	ISO 1133
FRR (MFR 21.6kg/ MFR 5kg)	5.4	-	ISO 1133
<b>Density</b>			
@23°C	954	kg/m <sup>3</sup>	ISO 1183
<b>MECHANICAL PROPERTIES <sup>(2)</sup></b>			
<b>Tensile modulus</b>	1230	MPa	ISO 527
<b>Tensile Impact Strength at -30°C (Notched)</b>	≥200	kJ/m <sup>2</sup>	ISO 8256
<b>FNCT (3.5 MPa, 2 % Igepal BC/9, 80°C) <sup>(2)</sup></b>	6	Hrs	ISO 16770

(1) Typical values: not to be construed as specification limits.

(2) Based on compression molded sheet.

### PROCESSING CONDITIONS

Recommended processing temperature: 180 - 220°C

### STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.