

# SABIC® HDPE CC860

HIGH DENSITY POLYETHYLENE

## DESCRIPTION

SABIC® HDPE CC860 is a high-density polyethylene especially developed for injection and compression molding of still water caps that meet organoleptic properties requirements. The material offers an ideal combination of rigidity, impact strength and low warpage.

## TYPICAL APPLICATIONS

- Caps & Closures for the packaging of still mineral water.
- Caps & Closures for beverage food and industrial packaging.

## TYPICAL PROPERTY VALUES

Revision 20230421

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES <sup>(1)</sup></b>			
<b>Melt Flow Rate (MFR)</b>			
@ 190°C & 2.16 kg load	7.0	g/10 min	ASTM D1238
<b>Density at 23°C</b>	957	kg/m <sup>3</sup>	ASTM D1505
<b>Sensoric (Organoleptic Properties)</b>	Approved	-	SABIC method
<b>MECHANICAL PROPERTIES <sup>(2)</sup></b>			
<b>Tensile test</b>			
Strength @ Yield	25	MPa	ASTM D638
Strength @ Break	10	MPa	ASTM D638
Elongation @ Break	>650	%	ASTM D638
<b>Flexural test</b>			
Flexural Strength	23	MPa	ASTM D790
Flexural Modulus	750	MPa	ASTM D790
<b>Izod impact notched</b>			
@ 23 °C	74	J/m	ASTM D256
<b>Hardness (Shore D)</b>	51	-	ASTM D2240
<b>ESCR (100% Igepal), F50 <sup>(3)</sup></b>	>4	Hrs	ASTM D1693B
<b>THERMAL PROPERTIES <sup>(1)</sup></b>			
<b>Vicat Softening Point</b>	127	°C	ASTM D1525
<b>Brittleness Temperature</b>	<-75	°C	ASTM D746

(1) Typical values: not to be construed as specification limits

(2) Based on Injection molded specimens.

(3) Based on compression molded sheet

## PROCESSING CONDITIONS

Barrel temperature: 200-250°C (390-480°F)

Mold temperature: 15-60°C (60-140°F)



## STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions, which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.