

SABIC® HDPE FI0750

HIGH DENSITY POLYETHYLENE

DESCRIPTION

SABIC® HDPE FI0750 is a high molecular High Density Polyethylene copolymer grade typically used for blown film applications. SABIC® HDPE FI0750 features are balance between toughness and stiffness, good impact properties with low gel level.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL APPLICATIONS

SABIC® HDPE FI0750 is typically used for blown film extrusion. Typical applications are heavy duty bags, grocery sacks, shopping bags, refuse bags, liners for multi-wall sacks and liners for frozen food meat. The grade can be blended with LLDPE and LDPE and can be used in co-extrusion process.

TYPICAL PROPERTY VALUES

Revision 20180807

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------|--------------|
| POLYMER PROPERTIES | | | |
| Melt Flow Rate (MFR) | | | |
| at 190 °C and 21.6 kg | 7.5 | g/10 min | ISO 1133 |
| at 190 °C and 5 kg | 0.22 | g/10 min | ISO 1133 |
| Density | 950 | kg/m ³ | ASTM D1505 |
| MECHANICAL PROPERTIES | | | |
| Hardness Shore D | 62 | - | ISO 868 |
| FILM PROPERTIES | | | |
| Tensile Properties ⁽¹⁾ | | | |
| stress at break, MD | 50 | MPa | ISO 527-3 |
| stress at break, TD | 45 | MPa | ISO 527-3 |
| strain at break, MD | 400 | % | ISO 527-3 |
| strain at break, TD | 450 | % | ISO 527-3 |
| Dart Impact Strength | | | |
| F50 | 240 | g | ASTM D1709 |
| Elmendorf Tear Strength | | | |
| MD | 250 | mN | ISO 6383-2 |
| TD | 450 | mN | ISO 6383-2 |
| THERMAL PROPERTIES | | | |
| Brittleness Temperature | <-80 | °C | ASTM D746 |
| Vicat Softening Temperature | | | |
| at 50 N (VST/B) | 75 | °C | ISO 306/B |

(1) Properties have been measured based on 20µm blown film with a BUR of 4 using 100% FI0750.

STORAGE AND HANDLING

Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC Europe considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC Europe whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

PROCESSING CONDITIONS

Processing conditions.

Melt Temperature: 200 - 225°C.

Frost Line Height: 6 - 8 times die cross-cut.

BUR: 3 - 5

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.