

# SABIC® HDPE P4808NA

HIGH DENSITY POLYETHYLENE FOR PIPE

## DESCRIPTION

P4808NA is a high density Polyethylene with multimodal distribution of the molecular mass. This is natural color grade suitable for non-pressure pipe applications.

It provides good ESCR (environmental stress cracking resistance)

## TYPICAL APPLICATIONS

P4808NA is a natural High Density Polyethylene (HDPE) resin specifically designed for non-pressure pipes such as Irrigation, cable conduits and Gravity pipes segment.

## TYPICAL PROPERTY VALUES

Revision 20210103

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR) <sup>(1)</sup></b>			
@ 190°C & 5 kg load <sup>(1)</sup>	0.23	g/10 min	ISO 1133
@ 190°C & 21.6 kg load	6.5	g/10 min	ISO 1133
<b>Density at 23°C</b>	949	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES</b>			
<b>Hardness (Shore D) <sup>(2)</sup></b>	>52	-	ASTM D2240
<b>Tensile Strength at Yield <sup>(3)</sup></b>	22	MPa	ASTM D638
<b>Tensile Elongation at Yield</b>	8	%	ISO 527-1/-2
<b>Tensile modulus</b>	850	MPa	ASTM D638
<b>Charpy Impact Notched @ 23°C</b>	23	kJ/m <sup>2</sup>	ISO 179
<b>Flexural Modulus</b>	820	MPa	ISO 178/1A
<b>Flexural Strength</b>	25	MPa	ISO 178
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Point @ 50N (VST/B)</b>	74	°C	ISO 306
<b>OIT (210°C)</b>	>20	Minutes	EN 728

(1) Typical values & not to be construed as specification limits.

(2) Test specimen according to ISO 527-2 type 1 BA, thickness 2mm with 50mm/min test speed.

(3) Based on compression molded sheet

## PROCESSING CONDITIONS

Typical processing conditions for P4808NA : Melt temperature: 190-220°C

## STORAGE AND HANDLING

Polyethylene material / compound should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions lead to quality deterioration and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.