



# Tangent <u>Structural</u> Lumber

Tangent's Structural Lumber has exceptional strength and stiffness, its flexural modulus of 650 ksi is far in excess of typical synthetic wood alternatives and allows for increased spans, greater load bearing capacity, a more solid feel and greater safety margins. Tangent's Structural Lumber is perfect for ground contact or wet environments without compromising its incredible durability.

#### STANDARD COLORS





Black

Gray



Norwegian Weatherwood

Custom colors available upon request

#### COMMON APPLICATIONS

- Decking Substructure
- Boardwalk Substructure
- Marine Dock Substructure
- Dodiawaik Substituctur
- Wide-Span Decking
- Trellises & Pergolas
- Posts & Piles



### TECHNICAL INFORMATION

| Properties   | ASTM  | Value/Units         |
|--|-------|---------------------|
| Specific Gravity   | D6111 | 1.18 SG             |
| Flexural Strength  | D6109 | 6,250 psi           |
| Flexural Modulus (Secant, at 1% strain)                            | D6109 | 650,000 psi         |
| Compressive Strength (Perpendicular to grain)                      | D6108 | 1,482 psi           |
| Compressive Modulus (Perpendicular to grain, Secant, at 1% strain) | D6108 | 54 ksi              |
| Coefficient of Thermal Expansion                                   | D6341 | 0.000033 in/in/°F   |
| Static Coefficient of Friction - Dry                               | D2047 | 0.73 average        |
| Static Coefficient of Friction - Wet                               | D2047 | 0.90 average        |
| Impact Resistance (Izod)   | D256  | 2.64 ft-lb/in       |
| Water Absorption   | D570  | 0.27% max by weight |
| Screw Withdrawal   | D6117 | 646 lbs             |
| Useful Temperature Range   |       | -40°F to +140°F     |

All above values shall be considered average except flexural strength. This value must have appropriate reduction factors set by the engineer of record.







| Material Property               | Description of Test Method  | ASTM   | Value/Units   |
|---------------------------------|---|--|---|
| Brittleness                     | Standard Test Method for Brittleness<br>Temperature of Plastics and Elastomers<br>by Impact               | D746-07  | No break at -40°F   |
| Density and<br>Specific Gravity | Standard Test Methods for Density<br>and Specific Gravity of Plastics by<br>Displacement                  | D792   | 74.0 lbs/cu.ft<br>0.043 lbs/cu.in<br>Specific Gravity: 1.18 |
| Hardness-Shore D                | Standard Test Method for Rubber<br>Property—Durometer Hardness  | D2240-<br>Type D                                   | 80  |
| Abrasion Resistance             | Standard Test Method for Abrasion<br>Resistance of Organic Coatings by<br>Taber Abraser                   | D4060<br>CS17 Wheel<br>10,000 cycles<br>2.2lb load | Weight Loss<br>0.023g / 0.043%                              |
| Ignition Temperature            | Standard Test Method for Determining Ignition Temperature of Plastics; Flash Point / Ignition Temperature | D1929-96   | >824°F (440°C)  |
| UV: Effect on Hardness          | Standard Practice for Florescent UV<br>Exposure of Plastics   | D4329 &<br>D2240                                   | 500 hrs: <1% Change in<br>Hardness                          |
| Chemical Resistance             | Standard Practices for Evaluation the<br>Resistance of Plastics to Chemical<br>Reagents                   | D543-06  | Sea Water: 0.06%<br>weight increase                         |
| Chemical Resistance             | Standard Practices for Evaluation the<br>Resistance of Plastics to Chemical<br>Reagents                   | D543-06  | Gasoline: 3.0%<br>weight increase                           |
| Chemical Resistance             | Standard Practices for Evaluation the<br>Resistance of Plastics to Chemical<br>Reagents                   | D543-06  | No.2 Diesel: 1.05%<br>weight increase                       |
| Flammability                    | Standard Test Method for Surface<br>Burning Characteristics of Building<br>Materials                      | E84-21a  | Flame spread index: 40<br>Smoke developed index: 300        |

Tangent Technologies, LLC, is a manufacturer of recycled plastic lumber. Tangent does not provide engineering services and assumes no responsibility, or liability, for any element of a projects design and/or construction details.

## **Tangent Structural Lumber (SL)**

Technical Data Sheet



# **Suitability and Limitations**

These products have greater impact resistance than wood but conversely less rigidity, and therefore prior to use a thorough design engineering study must be performed to determine the suitability of Tangent Structural Lumber in any critical application.

Fabrication is similar to wood and normal woodworking tools can be used. One should be advised that by transforming the product by drilling holes and routing edges the integrity and strength of the part can be altered. Eye protective wear, dusk masks, gloves and normal safety precautions must be used when handling and fabricating the product. (See SDS sheet for more details)

Inherent in Tangent Structural Lumber products, you will observe a greater coefficient of thermal expansion than stiffer wood products. Therefore, when designing your application, an accommodation must be made to properly allow for expected expansion and contraction over the length of the product.

Static electricity is a naturally occurring phenomenon to all resin-based products. On dry days there is potential to experience a static shock if you walk across Tangent Structural Lumber and touch a conducting surface such as a metal fixture. The physics is similar to walking across a carpet and receiving a shock when you touch a door handle. We do not warranty against static electricity as it is naturally occurring and is not a manufacturing defect. Contact our technical sales reps to learn how to minimize the generation of static electricity through product selection, available additives and construction details.

During winter conditions, you might find any surface made from Tangent Structural Lumber to be slippery in snow, wet and frost conditions. Unlike most other surfaces, you can easily spread rock salt or calcium chloride to restore decent traction and melt the frost or ice layer with no harmful effect to the Tangent Structural Lumber products.

### Warranty

Tangent Technologies LLC, the manufacturer of Tangent Structural Lumber products, offers a limited warranty that this product will not rot, splinter, decay or suffer structural damage directly from termites or fungal decay under normal use. Tangent Technologies LLC does not recommend or approve this product for all end use applications. The appropriate national and local code authorities should be consulted for safety, suitability and applicability for intended use prior to purchasing product. (See full warranty details)

This guideline and summary is intended to provide the distributor, installer and end user with basic guidelines and technical specifications for designing and properly installing the Tangent Structural Lumber products. However, the installer and/or purchaser of any Tangent Structural Lumber product is solely responsible for interpreting specific job conditions and determining the engineering design and suitability of end use and application of any Tangent Structural Lumber product. Adherence to applicable building and safety codes for specific locations and applications of this product are the sole responsibility of the installer and/or purchaser. In no event shall Tangent Technologies LLC, the manufacturer of the Tangent Structural Lumber products, be liable for labor, installation, reinstallation or for any indirect, punitive, exemplary or consequential damages of any kind whatsoever from the provisions of this information.

This revision 1.1 [8/06/24] supersedes all other Tangent Structural Lumber technical data sheets.

STD011-240806