



Titer Dtex	Tenacity CN/dtex	Modulus CN/dtex	Elongation %	Cut Length mm	Hot water Solubility 1 hr 90 °C - %
• 2.0 ± 0.25	• $\geq 11,5$	• ≥ 280	• $\leq 7,5$	• 5 or 6	• ≤ 2
3 years avarage	• 3 years avarage	• 3 years avarage	• 3 years avarage	• 3 years avarage	• 3 years avarage
• 2,1	• 12,3	• 300	• 6.7	• -	• 1

We have also different other grades of PVA fiber :

with higher tenacity , higher titer in different lenght from 4 to 12 mm