

## SALES SPECIFICATION

### Pure Acrylic 55%

#### Product Information

Chemical name: Acrylic Polymer Emulsion  
here to enter text.

CAS N°: Click or tap

Product name: Pure Acrylic 55%  
here to enter text.

HS code: Click or tap

#### General description

Methyl Ethyl Ketone Peroxide (Phthalate-Free) is a high-activity organic peroxide initiator used for the room-temperature curing of unsaturated polyester resins (UPR) in fiberglass-reinforced plastics, gelcoats, and castings. This phthalate-free grade offers an environmentally friendlier alternative while maintaining consistent performance and stability

#### Properties

Property	Value
Name	Pure Acrylic 55%
Visual Appearance	Milky White
Solids Content	55 ± 1%
Viscosity @ 30°C (RVT Spindle 4, 10 rpm)	400 – 600 cP
Monomer Content	< 0.3%
Minimum Film Forming Temperature	18°C
Film Properties	Highly Tacky, Flexible, Clear
pH	8.0 – 10.0

## Storage and handling:

- 12 months from the date of manufacture when stored under recommended conditions.
- Store in tightly closed containers in a cool, dry, and well-ventilated area.
- Avoid direct sunlight, heat, and freezing.
- Use appropriate PPE when handling.
- Agitate well before use, as settling may occur.