PRODUCT DATA SHEET

No : MDS/25-HK/224

Product : Garniture Tape

Brand : HooKSugen



ind . Hooksagen	
Туре	JHK-45.1
Material	Aramid Yarn / Kevlar (DUPONT)
Tape surface	Plain
Tape thickness	0.51 mm
Lateral tape flexibility	High
Temperature resistance	≥ 200 °C
Wear resistance	extreme
Breaking strength	≥ 4000 N/cm
Elongation of endless tape at 150 N/cm pre-tension	≤ 5.0%
Warp and weft density	≤ 0.1 weft
Service Life	≥ 10 hr
Coefficient of friction (1) To paper To Garniture	 0.40 ±0.05 (medium) 0.15 ±0.05 (very low)
Tolerances Length/mm (2) Width/mm (3) Thickness/mm (4) Swing/mm	 ±5.0 0 / -0.4 ±0.02 ≤ 0.8
Appearance	No edges, no fluonces
Recommended use tobacco transport (5)	Production of cigarettes, cigarillos, cigars and cigarette filters
Storage environment (1) > 0.79 = very high, 0.06 - 0.79 = high, 0.40 - 0.59 = medium, 0.2	 The temperature and humidity should be constant Avoid direct sunlight (will cause the strength decreasing

 $^{^{(1)}}$ > 0.79 = very high, 0.06 – 0.79 = high, 0.40 – 0.59 = medium, 0.20 – 0.39 = low, < 0.20 = very low

All data in this data-sheet correspond to the latest state of the art. Modifications are possible without prior notice. The values stated are for information only, they do not guarantee a specific property.

⁽²⁾ Length ranges from 2000 mm up to 7500 mm, other lengths on request

Width ranges from 9 mm up to +0.05, other width on request

⁽⁴⁾ At measured pressure of 0.5 N/cm²

⁽⁵⁾ The use in other fields requires former consultation