



RAHA SADR INDUSTRIAL CO

TECHNICAL DATA SHEET OF BITUMEN PENETRATION GRADE 50/70

BITUMEN 50/70	TEST METHOD	UNIT	SPECIFICATION
Penetration – 25°C, 100g, 5s	EN 1426	mm	50-70
Softening Point (Ring & Ball)	EN 1427	°C	46/54
Kinematic Viscosity @ 135°C	EN 12595	mm ² /s	295 Min
Penetration Index	EN 12591	-	-1.5 +0.7
Solubility in Xylene	EN 12592	%	99 Min
Flashpoint (Cleveland Open)	EN 22592	°C	230 Min
Resistance to Hardening at 163 °C			
Change in mass (m/m)	EN12607-1	%	0.5 Max
Retained Penetration 25°C, 100g, 5s (% of original)	EN 1426	%	50 Min
Increase in softening point	EN 1427	°C	11 Max
Spot test	A.a.s.h.o.t102	-	Negative
Wax Content	EN 12606-1	(%)	2.2 max

PACKING:

Bulk
180 kg New Steel Drum
1 MT Jumbo Bag
300 kg Bitubag



Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran



+983132355207
+983132355214



info@rahaoil.com



www.rahaoil.com