



RAHA SADR INDUSTRIAL CO

TECHNICAL DATA SHEET OF BITUMEN PENETRATION GRADE 85/100

BITUMEN 85/100	TEST METHOD	UNIT	SPECIFICATION
Specific gravity @ 25°C	ASTM D70	kg/cm ³	1.01/1.06
Penetration @ 25°C	ASTM D5	mm/10	85/100
Softening point °C	ASTM D36	°C	41/49
Ductility @25 °C	ASTM D113	cm	100 min
Loss on heating(wt) %	ASTM D6	wt %	0.2 max
Drop in penetration after heating %	ASTM D5-D6	%	20 max
Flashpoint °C	ASTM D92	°C	250 min
Solubility in CS ₂ wt %	ASTM D4	wt %	99.5 max
Spot test	A.a.s.h.o.t102	-	Negative

PACKING:

Bulk
180 kg New Steel Drum



Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran



+983132355207
+983132355214



info@rahaoil.com



www.rahaoil.com