

ULTRA SS308LT1-1

FLUX CORED WIRE

Hardfacing Wire for Extreme Abrasion
Resistance

CLASSIFICATION:

- T 23 12 L R C/M 1
- EN ISO 17633-A
- TS308LT1-1
- AWS A/SFA 5.22
- SS308LT1-1

TYPICAL APPLICATIONS:

- Food & beverage equipment
- Pharmaceutical machinery
- Pressure vessels
- Chemical tanks
- Stainless steel structures
- Marine and offshore industries

KEY FEATURES:

- All position capability
- Rutile type gas shielded FCW wire
- Easy slag removal, smooth weld bead
- Suitable for single and multi-pass welds
- Low fumes, Minimal spatters, High deposition rate

TYPICAL CHEMICAL COMPOSITION OF UNDILUTED WELD METAL WT (%):

C – 0.03	Mn – 1.8	Si – 0.5	Cr – 19.5	Ni – 10.2	
----------	----------	----------	-----------	-----------	--

MECHANICAL PROPERTIES OF ALL WELD METAL:

Condition	UTS, Mpa	YS at 0.2% offset, Mpa	EL%	CVN Impact, J at
As Welded	570	420	28	20°C

PARAMETERS & PACKING DATA:

Ø x L mm	Amperage, A
1.2	130-280
1.6	200-360

DCEP(Electrode Positive)

Use 1-2 volts lower when using mix shielding gas

Available in Vacuum Pack of 15 kg wire layer wounded on Plastic Spool.



DCEP

Electrode Positive

All positions except vertical down



**Use 1-2 volts lower when using
mix shielding gas**