












龍 記 鋼 材  
LUNG KEE STEEL



ISO 9001  
Approval  
Certificate  
No: HKG0991050

LKM STEEL RAINBOW CHART

10-2015

Manufacturer	Material Grade	Comparable Standard			Delivered Hardness from Steel Mill (Surface)	Characteristics	Typical Analysis of Major Chemical Contents								Applications	
		AISI	JIS	W.Nr			C	Si	Cr	Ni	Mn	Mo	V	W		
	AUBERT & DUVAL															
	ADC3	H11 Modified High Purity Process	SKD6 Modified High Purity Process	1.2340 High Purity Process	Annealed to HB235	High purity, better toughness and thermal conductivity than common hot work steels, excellent resistance to heat checking, outstanding hardenability, good dimensional stability during hardening process	0.35	-	5.0	-	-	1.3	0.4	-	-	Large size light-alloy die casting die with long production run
	ASSAB															
	718H (IMPAX HI HARD)	P20 Modified	-	1.2738	Prehardened to HB330 ~ 380	Homogenous microstructure, stable quality, good texturing and EDM property	0.38	0.3	2.0	1.0	1.4	0.2	-	-	-	Plastic injection mould for medium production run and PS, PE, PP, ABS and other non-corrosive resins
	NIMAX	Special Steel			Prehardened to HB360 ~ 400	Good polishing and texturing properties. Superior EDM-ability and machinability. High toughness and good weldability	0.1	-	3.0	1.0	2.5	-	-	-	-	Plastic injection mould for various applications such as LCD TV panels, interior part for automobile, engineering components and those resins without corrosive property
	S136 (STAVAX ESR)	420 Modified ESR	SUS420J2 Modified ESR	1.2083 Modified ESR	Annealed to HB200	High purity with fine microstructure, can be polished to mirror finish. Excellent corrosion resistance and low deformation during heat treatment	0.38	0.8	13.6	-	0.5	-	0.3	-	-	Plastic injection mould with small to medium size, long production run and high polishing requirement, e.g. PMMA, PC, resins such as PVC, PA, POM or additives with corrosive property, machine part for food processing machinery
	S136H (STAVAX ESR (PRE-HARDENED))				Prehardened to HB290 ~ 330											Plastic injection mould with small to medium size, medium production run and high polishing requirement, e.g. PMMA, PC, resins such as PVC, PA, POM or additives with corrosive property, machine part for food processing machinery
	S136 SUP (MIRRAX ESR)	420 Modified ESR	SUS420J2 Modified ESR	1.2083 Modified ESR	Annealed to HB250(max)	Improved version of S136 with better corrosion resistance and toughness	0.24	-	13.3	1.4	0.5	0.35	0.35	-	-	Large size and complicated structure plastic mould for PMMA, PC, PVC, PA, POM plastics and machine part for food processing machinery
	S136H SUP (MIRRAX ESR (PRE-HARDENED))				Prehardened to HB290 ~ 330	Improved version of S136H with better corrosion resistance and toughness										
	POLMAX	420 Modified ESR+VAR	SUS420J2 Modified ESR+VAR	1.2083 Modified ESR+VAR	Annealed to HB200	Ultra-high purity and extremely low segregation by double remelting process (ESR+VAR). Superb polishability to attain optical standard. Good corrosion resistance and low deformation during heat treatment	0.38	0.9	13.6	-	0.5	-	0.3	-	-	High quality moulds for Lens, optical products, compact discs and medical applications
	ROYALLOY	Special Stainless Steel			Prehardened to HB290 ~ 330	Superior machinability, good corrosion resistance, uniform and consistent hardness in every dimension, excellent weldability	0.05	0.4	12.6	-	1.2	-	-	-	-	Mould base of plastic mould with requirement of long run, corrosion resistance and high precision; also suitable for plastic and rubber moulds, machine part with low requirement on polishability and texturing
	8418 (DIEVAR)	Special Steel			Annealed to HB160	High purity, good high-temperature strength, outstanding temperature resistance and excellent resistance to heat checking, excellent hardenability, good dimensional stability during hardening	0.35	0.2	5.0	-	0.75	2.3	0.8	-	-	High demand light-alloy die casting die, hot forging inserts, extrusion dies with long production run
	8407 (ORVAR SUPREME)	H13 Modified ESR	SKD61 Modified ESR	1.2344 Modified ESR	Annealed to HB185	High purity, high toughness and good resistance to thermal fatigue	0.38	1.0	5.3	-	0.4	1.3	0.9	-	-	Die casting die, extrusion die, through-hardened plastic mould for PA, POM,PS, PE, EP and other non-corrosive plastics
	635 (CALMAX)	High wear resistance multi-functional tool steel			Annealed to HB200	Combining with high toughness and high wear resistance; good hardenability and can be flame-hardening to HRC56~60 with harden layer up to 5mm thick	0.6	0.35	4.5	-	0.8	0.5	0.2	-	-	Heavy duty blanking, forming tool or coining tool requiring good adhesive wear resistance; also suitable for moulding fibre-reinforce plastics
	DAIDO STEEL															
	PAC5000	P20 Modified	-	1.2311 Modified	Prehardened to HB336 ~ 362	Patent composition to reduce cracking during welding process; homogenous structure and hardness; good texturing property; can be polished up to #5000	Patent Pending								Plastic injection mould for medium production run with high texturing requirement such as housing for Office Equipment, Copier, Printer; not suitable for moulding corrosive resins	
	NAK80	P21 Modified VAR	-	-	Prehardened to HB344 ~ 400	Age hardening steel with high delivery hardness; excellent texturing and EDM properties; can be polished up to #8000	0.15	0.3	-	3.0	1.5	0.3	-	-	-	Plastic injection mould for medium production run with high polishing and texturing requirement; not suitable for moulding corrosive resins
	PAT868	Special Steel			Annealed to HB229(max)	Special alloying design and steel making process to provide the material with integrated properties of high toughness, anti-corrosion and mirror polishability	Patent Pending								Plastic injection mould with the adoption of rapid heat and cool technology, mould insert or slider for long production run with complicated mould design and high polishing or texturing requirement	
	S-STAR	420 Modified ESR	SUS420J2 Modified ESR	1.2083 Modified ESR	Prehardened to HB300 ~ 330	High purity with fine microstructure, can be polished to mirror finish. Excellent corrosion resistance and low deformation during heat treatment	0.38	0.9	13.5	-	-	0.1	0.3	-	-	Plastic injection mould with small to medium size, long production run and high polishing requirement, e.g. PMMA, PC, resins such as PVC, PA, POM or additives with corrosive property, machine part for food processing machinery
	S-STAR-A	420 Modified ESR	SUS420J2 Modified ESR	1.2083 Modified ESR	Annealed to HB229(max)											Plastic injection mould with small to medium size, medium production run and high polishing requirement, e.g. PMMA, PC, resins such as PVC, PA, POM or additives with corrosive property, machine part for food processing machinery
	DH31-S	Special Steel			Annealed to HB235(max)	Good through-hardening property, high resistance to thermal fatigue and hot erosion	Patent Pending								Small to medium size Al and Mg alloy die casting die, component for die casting die, Al alloy extrusion die	
	DHA1	H13	SKD61	1.2344	Annealed to HB229(max)	Good toughness and resistance to thermal fatigue	0.38	0.9	5.0	-	0.4	1.3	1.0	-	-	Small size Zn alloy die casting die, component for die casting die, Al alloy extrusion die, through-hardened plastic injection mould
	DHA-WORLD	H11 Modified	SKD6 Modified	1.2343 Modified	Annealed to HB229(max)	Excellent through-hardening property, high resistance to thermal fatigue and hot erosion	Patent Pending								Medium to big sizes Al and Mg alloy die casting die with medium to long production run	
	DH31-EX	Special Steel			Annealed to HB235(max)	Excellent through-hardening property and toughness, excellent resistance to thermal shock and thermal fatigue, high hot strength and fracture toughness, superior resistance to heat checking and hot erosion	Patent Pending								Big sizes Al and Mg alloy die casting die with long production run	
	DC53	D2 Modified	SKD11 Modified	1.2379 Modified	Annealed to HB255	Toughness is better than that of conventional SKD11; hardness can be attained to around HRC62 after high-temperature tempering, which massively reduces the risk of cracking during wire-cutting (WEDM) or grinding processes; suitable for surface treatment	Patent Pending								Cold work dies for stamping, forming, deep drawing, rolling	
		GROEDITZ														
XPM		P20 Modified	-	1.2738 Modified	Prehardened to HB359 ~ 400 (HRC38 ~ 42)	Homogenous hardness, improved properties such as machinability, thermal conductivity, polishability, texturing property and weldability over normal AISI P20 tool steel	0.27	0.3	1.35	1.00	1.55	0.5	-	-	-	Large size plastic injection mould for car bumper, dashboard and housing for photocopier and printer; not suitable for moulding corrosive resins
XPM V ESR		P20 Modified ESR	-	1.2738 Modified ESR	Prehardened to HB341 ~ 400 (HRC36 ~ 42)	ESR version of XPM. Reduction of anisotropy, impurities and segregation to provide better polishability	0.27	0.3	1.35	1.00	1.55	0.5	-	-	-	Large size plastic injection mould that requires high surface quality, such as automobile headlights, rear view mirror, decorative part, housing for lighting, LCD/LED TV, photocopier and printer; not suitable for moulding corrosive resins
SWG 2083mod V ESR		420 Modified ESR	SUS420J2 Modified ESR	1.2083 Modified ESR	Annealed to HB241(max)	Good corrosion resistance, high wear resistance, better mirror polishability than SWG2083	0.38	1.0	13.0	-	0.5	-	0.25	-	-	Plastic injection mould for PVC, PP, EP,PC, PMMA with long production run and requiring high surface finish
SWG 2343 V ESR		H11 ESR	SKD6 ESR	W.Nr 1.2343 ESR	Annealed to HB 225(Max)	Homogenous structure and good isotropic property. High toughness and good heat resistance, good resistance to heat checking, excellent through hardening property and mirror polishability.	0.36	1.0	5.0	-	0.4	1.2	0.4	-	-	Light-alloy die casting die, Al alloy extrusion die, components for die casting, e.g. nozzles; through-hardened plastic injection mould with high surface finish requirement and moulding non-corrosive resins, car lighting mould
LKM also provides SWG738, SWG738H, SWG2711, SWG2083, SWG2083H, SWG2316, SWG2316H, SWG2344, SWG2344 ESR, SWG2343&SWG2767 on stock. For inquiry, please contact our Sales or Steel Marketing department.																
	LKM SPECIAL STEEL															
	LKM P20M (Old Name : LKM P20 FORGE)	P20 Modified	-	1.2311 Modified	Prehardened to HB260 ~ 350	Economical choice of pre-hardened plastic mould steel	Undisclosed								Mould base/plate with high strength requirement for plastic injection mould; core/movable part of plastic injection mould without high surface finish requirement	
	LKM2311	P20	-	1.2311	Prehardened to HB280 ~ 325	Pre-hardened plastic mould steel	0.37	-	1.9	-	1.45	0.2	-	-	-	Mould base/plate with high strength requirement for plastic injection mould; core/movable part of plastic injection mould without high surface finish requirement
	LKM2312	P20+S	-	1.2312	Prehardened to HB280 ~ 325	Excellent machinability	0.37	-	1.9	-	1.45	0.2	-	-	-	Mould base/plate with requirement of high strength and high volume/speed machining for plastic injection mould
	LKM738	P20 Modified	-	1.2738	Prehardened to HB290 ~ 330	Modified version of conventional AISI P20 plastic mould steel with Ni added to increase through hardening property	0.37	0.2	2.0	1.0	1.1	0.25	-	-	-	Plastic injection mould for medium production run and PS, PE, PP, ABS and other non-corrosive resins
	LKM738H				Prehardened to HB330 ~ 370											
	LKM838HS	P20 Modified	-	1.2738 Modified	Prehardened to HB330 ~ 370	With special adjustment to the chemical composition and steel making process, LKM838HS possesses better polishability, EDM and texturing properties, weldability, thermal conductivity than conventional W.Nr 1.2738HH plastic mould steel	Patent Pending								Plastic injection mould for medium production run with good texturing property, e.g. car bumper, dashboard and housing for photocopier and printer; not suitable for moulding corrosive resins	
	LKM2711	-	-	1.2711	Prehardened to HB335 ~ 385	Combining high yield strength and good toughness; suitable for nitriding	0.55	-	0.7	1.7	0.8	0.25	-	-	-	Plastic injection mould for medium production run and PS, PE, PP, ABS and other non-corrosive resins
	LKM808ESR (Old Name : LKM808E)	P21 Modified ESR	-	-	Prehardened to HB360 ~ 415	Age hardening steel with high delivery hardness, good polishability and texturing property	0.1	-	-	3.0	1.5	0.25	-	-	-	Plastic injection mould for medium production run with simple geometry design; not suitable for moulding corrosive resins
	LKM2083	420	SUS420J2	1.2083	Annealed to HB240(max)	Working in through hardening condition with good corrosion resistance, wear resistance and polishability	0.43	-	13.0	-	0.3	Some	-	-	-	Plastic injection mould for moulding resins such as PA, POM and flame retarding additives and long production run
	LKM2083H				Prehardened to HB280 ~ 320	Pre-hardened corrosion stainless steel										Plastic injection mould for moulding resins such as PA, POM and flame retarding additives and medium production run
	LKM2083 ESR	420 Modified ESR	SUS420J2 Modified ESR	1.2083 Modified ESR	Annealed to HB250(max)	Good corrosion resistance, high wear resistance, better mirror polishability than LKM2083	0.38	0.9	13.0	-	0.5	-	Some	-	-	Plastic injection mould for PVC, PP, EP, PC, PMMA with long production run and requiring high surface finish
	LKM2316	-	-	1.2316	Annealed to HB250(max)	Working hardness can be attained to HRC44~47. Excellent corrosion resistance	0.4	-	16.0	Some	0.5	1.0	-	-	-	Plastic injection mould for PVC and other high corrosive resins with requirement of long production run; components for injection moulding machine and machine part for food processing machinery
	LKM2316H				Prehardened to HB265 ~ 340	Pre-hardened high corrosion resistance steel										Plastic injection mould for PVC and other high corrosive resins with requirement of medium production run; components for injection moulding machine and machine part for food processing machinery
	LKM2343	H11	SKD6	1.2343	Annealed to HB225(max)	High toughness and good heat resistance; good resistance to heat checking and good through hardening property	0.36	1.0	5.0	-	0.4	1.2	0.35	-	-	Light-alloy die casting die, Al alloy extrusion die, components for die casting, e.g. nozzles; through-hardened plastic injection mould for non-corrosive resins
	LKM2343 ESR	H11 ESR	SKD6 ESR	1.2343 ESR	Annealed to HB225(max)	Homogenous structure and good isotropic property. High toughness and good heat resistance, good resistance to heat checking, excellent through hardening property and mirror polishability	0.36	1.0	5.0	-	0.4	1.2	0.35	-	-	Light-alloy die casting die, Al alloy extrusion die, components for die casting, e.g. nozzles; through-hardened plastic injection mould for non-corrosive resins with high surface finish requirement
	LKM2344	H13	SKD61	1.2344	Annealed to HB225(max)	High toughness and good heat resistance, good resistance to heat checking and through hardening property	0.38	1.0	5.0	-	0.4	1.3	1.0	-	-	Light-alloy die casting die, Al alloy extrusion die, components for die casting, e.g. nozzles; through-hardened plastic injection mould for non-corrosive resins
	LKM2344 ESR	H13 ESR	SKD61 ESR	1.2344 ESR	Annealed to HB225(max)	Homogenous structure and good isotropic property. High toughness and good heat resistance, good resistance to heat checking, excellent through hardening property and mirror polishability										Light-alloy die casting die, Al alloy extrusion die, components for die casting, e.g. nozzles; through-hardened plastic injection mould for non-corrosive resins with high surface finish requirement
	LKM2510	O1	SKS3	1.2510	Annealed to HB230	Working in through hardening condition with good wear resistance	0.93	-	0.6	-	1.1	-	0.1	0.6	-	Dies for shearing blade, cold forming, blanking and punching for small to medium production run; measuring tool; slider and wedge block for plastic injection mould
	LKM2767	6F7	-	1.2767	Annealed to HB262(max)	Working in through hardening condition with high toughness	0.45	-	1.4	4.1	-	0.3	-	-	-	Small to medium size of through-hardened plastic injection mould with complicated structure; dies for shearing and blanking of sheet metal with 10mm thick or above
	SINTO															
	PORCERAX II PM - 35	Sintering powder metallurgical porous material			Prehardened to HV350 ~ 400	Porous material with high corrosion resistance, high machinability and EDM property (supplied with 7 µm pore size)	0.02	0.07	16.5	12	0.17	1.9	-	-	-	Insert for plastic injection mould to solve the problem of gas trapping during production
	MATERION															
	MOLDMAX HH	UNS C17200			Prehardened to HRC36 ~ 42	High strength beryllium copper alloy, high thermal conductivity and high hardness, shortening moulding cycle	Be1.9	Co+N10.25		Cu 97.85						
	EDM COPPER															
	LKM C1100P	JIS H3100			-	Extremely high purity, good electrical conductivity, high machinability, low thermal deformation	Cu 99.95								EDM copper electrode	
	CHINA MADE TOOL STEEL															
	CN P20 MOD (Old Name : LKM P20(MOD))	P20 Modified	-	1.2311 Modified	Prehardened to HB250 ~ 360	Economical choice of pre-hardened plastic mould steel	Undisclosed								Mould base/plate with high strength requirement for plastic injection mould; core/movable part of plastic injection mould without high surface finish requirement	
	CN2311 (Old Name : WY2311)	~P20	-	~1.2311	Prehardened to HB260 ~ 340	Prehardened plastic mould steel	0.37	-	1.7	-	1.4	0.25	-	-	-	Mould base/plate with high strength requirement for plastic injection mould; core/movable part of plastic injection mould without high surface finish requirement
	CN718 (Old Name : WY718)	P20 Modified	-	~1.2738	Prehardened to HB280 ~ 330	Prehardened plastic mould steel, hardness homogeneity is better than normal AISI P20 plastic mould steel	0.37	-	1.8	1.0	1.4	0.25	-	-	-	Mould base/plate with high strength requirement for plastic injection mould; core/movable part of plastic injection mould without high surface finish requirement
	CN718H (Old Name : WY718H)				Prehardened to HB330 ~ 380											
	CN420 (Old Name : LKM420)	~420	~SUS420J2	~1.2083	Annealed to HB240(max)	Good anti-rusting property	0.38	-	13.0	-	0.5	-	-	-	-	Plastic injection mould for long production run with simple geometry and anti-rusting property but without high surface finish requirement
	CN420H (Old Name : LKM420H)	~420	~SUS420J2	~1.2083	Prehardened to HB280 ~ 330	Pre-hardened stainless steel	0.38	-	13.0	1.0	0.5	-	-	-	-	Plastic injection mould for small to medium production run with simple geometry and anti-rusting property but without high surface finish requirement; suitable for mould base/plate with anti-rusting property
	CN H13 (Old Name : LKM H13)	~H13	~SKD61	~1.2344	Annealed to HB225(max)	Economical choice of hot work steel	0.38	1.0	5.0	-	0.4	1.3	1.0	-	-	Through-hardened plastic injection mould for those non-corrosive resins; slider and lifter for plastic injection mould; small size of Zn die casting die for small to medium production run
PLAIN CARBON STEEL																
S45C ~ S50C	1045 ~ 1050	S45C ~ S50C	~1.1730	Annealed to HB170 ~ 220	Good machinability	0.5	0.35	-	-	0.8	-	-	-	-	-	Mould base/plate for plastic injection mould and machinery part