

Prada



yugos upholstery



Camel



Red




Champignon



Brick



Iguana



Dark Brown



Savana



Canary

Prada



yugos upholstery



Hermes



Nugget



grey



Silver Grey



Apricot



Black



Cream



Dark Grey



Coffee



Caramel



Beige

S.LEATHER CARE INSTRUCTIONS



yugos upholstery

DO / LAKUKAN

- Wipe regularly with a soft dry or damp cloth.
Lap rutin dengan kain lembut kering atau lembap.
- Clean spills immediately with mild soap & water.
Segera bersihkan tumpahan dengan sabun lembut dan air.
- Keep away from direct sunlight & heat.
Jauhkan dari sinar matahari dan panas langsung.
- Air dry naturally.
Keringkan secara alami.
- Use cleaner or conditioner for synthetic leather.
Gunakan pembersih atau kondisioner khusus kulit sintetis.

S.LEATHER CARE INSTRUCTIONS



yugos upholstery

DONT'S / JANGAN LAKUKAN

- Don't use alcohol, acetone, or harsh chemicals.
Jangan gunakan alkohol, aseton, atau bahan kimia keras.
- Don't scrub or use abrasive tools.
Jangan digosok keras atau gunakan alat abrasif.
- Don't soak with water.
Jangan direndam dengan air.
- Don't place sharp or heavy objects.
Jangan letakkan benda tajam atau berat.



TECHNICAL SPECIFICATION:

| NO. | UNITS | | METHOD |
|---|--------------------|--------------------------------|--|
| 1. WIDTH | MM | MIN. 1370 | ASTM D751-06 |
| 2. THICKNESS | MM | 1,15 - 1,25 | ASTM D751-06 |
| 3. WEIGHT | GR/M ² | 520 - 580 | ASTM D751-06 |
| 4. BOND TRENGTH | KGF/M ² | MIN. 1,5 | ASTM D751-06 |
| 5. BREAKING STRENGTH: | | | |
| - WRAP | KGF/2 INCH | MIN. 80 | ASTM D751-06 |
| - WEFT | KGF/2 INCH | MIN. 50 | |
| 6. TEAR STRENGTH: | | | |
| - WRAP | KG | MIN. 3 | ASTM D2261-02 |
| - WEFT | KG | MIN. 3 | |
| 7. ELONGATION (UNDER 14 KG) | % | 80 -160 | ASTM D751-06 |
| 8. STRETCH (AT 12 KG): | | | SOCIETY OF AUTO ENGINEERS / METHOD J-855 |
| - WRAP | % | 10 - 40 | |
| - WEFT | % | 100 - 200 | |
| 9. PERMANENT SET: | | | SOCIETY OF AUTO ENGINEERS / METHOD J-855 |
| - WRAP | % | MAX. 5 | |
| - WEFT | % | MAX. 20 | |
| 10. GRAIN RETENTION (105°C; 15 MIN) | - | NO LOSS OF GRAIN | FACTORY TEST |
| 11. FLEXIBILITY | CYCLES | MIN. 400.000 | ASTM D2097-03 |
| 12. FOLDING TEST 24 HRS: ROOM TEMPERATURE OVEN TEMP. 60°C | - | NO CREASE WHITENING | FACTORY TEST |
| 13. TABER ABRATION CS/10/1000 GM 400 CYCLES | - | NO OBJECTIONAL COLOR CHANGE | ASTM D3389-05 |
| 14. COMPOSITION : | | | |
| POLYESTER | - | 20,7% | - |
| PVC | | 79% | |
| ACRYLIC | | 0,3% | |

Colour may vary from one production lot to another.