


Tenun




yugos upholstery




Sunset




Late




Vanilla



Fog



Smoke



Blue Lagoon



Lime

S.LEATHER CARE INSTRUCTIONS



yugos upholstery

DO / LAKUKAN

- Wipe regularly with a soft dry or damp cloth.
Lap rutin dengan kain lembut kering atau lembap.
- Clean spills immediately with mild soap & water.
Segera bersihkan tumpahan dengan sabun lembut dan air.
- Keep away from direct sunlight & heat.
Jauhkan dari sinar matahari dan panas langsung.
- Air dry naturally.
Keringkan secara alami.
- Use cleaner or conditioner for synthetic leather.
Gunakan pembersih atau kondisioner khusus kulit sintetis.

S.LEATHER CARE INSTRUCTIONS



yugos upholstery

DONT'S / JANGAN LAKUKAN

- Don't use alcohol, acetone, or harsh chemicals.
Jangan gunakan alkohol, aseton, atau bahan kimia keras.
- Don't scrub or use abrasive tools.
Jangan digosok keras atau gunakan alat abrasif.
- Don't soak with water.
Jangan direndam dengan air.
- Don't place sharp or heavy objects.
Jangan letakkan benda tajam atau berat.



TECHNICAL SPECIFICATION:

NO.	UNITS		METHOD
1. WIDTH	MM	MIN. 1370	ASTM D751-06
2. THICKNESS	MM	1.15 - 1.25	ASTM D751-06
3. WEIGHT	GR/M ²	520 - 580	ASTM D751-06
4. BOND STRENGTH	KGF/2. CM	MIN. 1.5	ASTM D751-06
5. BREAKING STRENGTH : WRAP WEFT	KG/2 INCH KG/2 INCH	MIN. 60 MIN. 50	ASTM D751-06
6. TEAR STRENGTH : WRAP WEFT	KG KG	MIN. 3 MIN. 3	ASTM D2261-02
7. ELONGATION (UNDER 14 KG)	%	100 - 180	ASTM D751-06
8. STRETCH (AT 17 KG): WRAP WEFT	% %	10 - 40 100 - 200	SOCIETY OF AUTO ENGINEERS / METHOD J-855
9. PERMANENT SET : WRAP WEFT	% %	MAX. 5 MAX. 40	SOCIETY OF AUTO ENGINEERS / METHOD J-855
10. GRAIN RETENTION (105° C, 15 MIN)	-	NO LOSS OF GRAIN	FACTORY TEST
11. FLEXIBILITY	CYCLES	MIN. 400.000	ASTM D2097-03
12. FOLDING TEST (24 HRS) ROOM TEMPERATURE OVEN TEMP. 60° C	-	NO CREASE WHITENING NO CREASE WHITENING	FACTORY TEST
13. TABER ABRATION CS/10/1000 GM 400 CYCLES	-	NO OBJECTIONAL COLOR CHANGE	ASTM D3389 - 05
14. FADE RESISTANCE (UV TEST) 100 & 200 HOURS	-	NO COLOR CHANGE	ASTM G155 ISO 105-B02

colour may vary from one production lot to another.

Synthetic Leather Design Guide:

vertical on length



1.40 M
WIDTH

LENGTH